



Creative Materials, Inc.
141 Middlesex Road
Tyngsboro, MA 01879

T 978.649.4700
F 978.649.2040

123-36

SPRAYABLE, PLATEABLE, ELECTRICALLY CONDUCTIVE INK

DESCRIPTION: 123-36 is a sprayable, electrically conductive ink and coating which is suitable for applications requiring subsequent plating operations. The product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to abrasion, scratching and thermal aging. Some applications for 123-36 include, but are not limited to, electroless, and electrolytic plating, anode and cathode coatings for capacitors, emi/rfi shielding and as an underlying coating to prepare surfaces for plating and subsequent soldering. 123-36 can also be used as an underlying coating for decorative plating on various substrates. 123-36 is a sprayable version of 117-31.

TYPICAL PROPERTIES:

Viscosity (cps)	800
Filler	Silver
Percent Silver (cured)	> 78
Volume Resistance, max. (Ω -cm)	0.0001
Solderable	No
Hydrolytic Stability	Excellent
Useful Temperature Range ($^{\circ}$ C)	-55 to 200
Thermal Stability ($^{\circ}$ C)	Good to 325

SUGGESTED HANDLING & CURING: 123-36 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI Thinner #113-39 or for slower drying CMI Thinner# 114-20. Prior to using, be certain to re-suspend silver. Best properties, for most applications, result when cured for 1 hour at 175 $^{\circ}$ C. Good properties are obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 150 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: 3 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.

REVISION DATE: 3/16/04 REVISION: A